

Lubricants for elastic fiber

Publication number: TW562889 (B)

Publication date: 2003-11-21

Inventor(s): AZUSE IKUNORI [JP]; WAKAHARA YOSHIYUKI [JP]

Applicant(s): SANYO CHEMICAL IND LTD [JP]

Classification:


- **international:** *D06M13/188; D06M13/342; D06M13/463; D06M15/19; D06M15/53; D06M15/643; D06M13/00; D06M15/19; D06M15/37;* (IPC1-7): D06M13/463


- **European:** C10M1/08T; D06M13/188; D06M13/342; D06M13/463; D06M15/19; D06M15/53; D06M15/643


Application number: TW20010118540 20010731


Priority number(s): JP20000230514 20000731; JP20000331809 20001031; JP20010076728 20010316

Also published as:

 US2003024052 (A1)

 US6821301 (B2)

 WO0210500 (A1)

 CN1386150 (A)

Abstract of TW 562889 (B)

The present invention provides a lubricant for elastic fibers which comprises an amphoteric surfactant (A1) and/or a cationic surfactant (A2) as well as a base oil (B) and has a surface tension thereof at 25 DEG C of 14 to 35 mN/m and a volume resistivity thereof at 20 DEG C of 1×10^7 to 1×10^{13} $\Omega \cdot \text{cm}$; a lubricant for elastic fibers which comprises an ionic surfactant (A) and a base oil (B) and has a surface tension (S) thereof at 25 DEG C of 14 to 22.5 mN/m and a volume resistivity (ρ) thereof at 20 DEG C of 1×10^7 to 1×10^{13} $\Omega \cdot \text{cm}$, ρ and S satisfying the following relation [1]: $\rho \leq 1 \times 10^{(-2.4S+61)}$; a spin finish for elastic fibers which comprises a quaternary ammonium salt of the specific composition, a base oil and a higher fatty acid (C5-30) metal salt powder; ; a method of treating an elastic fiber which comprises providing an elastic fiber with any of the above lubricant for elastic fibers in an amount of 0.1 to 12% by weight of said fiber; and an elastic fiber which is obtainable by the above treatment method.

Data supplied from the **esp@cenet** database — Worldwide